



Technical info

90 mic Barrier Film
7 layer PA/PA/PE BLOWN FILM
Excellent Sealability
Excellent Mechanical properties

SR.NO	Property	Value
1	AVG. THICKNESS (Mic)	90 (3.6 Mil)
2	DART IMPACT (gm at 66 cm)	800
3	TENSILE (N/15mm) MD TD	47 34
4	ELONG (%) MD TD	621 497
5	C.O.F. (F → F) OUTER INNER	0.414 0.231
6	SEAL STRENGHT (N/15mm)	24.74
7	OTR (23 deg c) DRY (cc/m2/day)	40
8	WVTR (90 % RH ,38 deg c)	3.5

Film complies with FDA, EC relevant regulations -food grade film.

This is to certify that the raw material (inputs) such as polymers, pigments, used in the above products are of virgin and food grade quality and also acceptable for incidental food contact and does not contain any substance which is listed in the negative lists. It also conforms to the positive list of constituents as prescribed the inputs incorporated in it also comply with FDA: CFR, title 21,177.1520 olefin polymer & EC 2002/72/ec,as amend up to EC directive 2005/79/EC – food grade

Typical values not specified limits.

Vishakha assumes no liability for use of this data sheet.

These results contained in this test certificate are intended only for the guidance and not valid for legal purposes or for advertisement.