

# Product Specification



Adding  
Value  
to Food

Product Title CLING FILM KOEX 450MM x 1500M 12 MICRON

Product Code K12500

## 1 Product and producer's identification

- **Product description:** transparent plastic material, unprinted, PVC – P (plasticized polyvinyl chloride) film structured in reels of several widths.

## 2 Product characteristics

- **Chemical composition:** Polyvinyl chloride (PVC) with plasticizers, anti-oxidants and stabilizers. All these raw materials are suitable for the foodstuffs contact; chlorine content: 37 – 38 %
- **Film type:** Extensible double-layer with antifog effect
- **Reel inner cardboard core diameter:** 112,0 – 112,7 mm
- **Reel outer core diameter:** 230 mm (max)
- **Physical data:**

Parameter	Unit of measure	Method	KOEX 810 10 µm	KOEX 811 11 µm	KOEX 812 12 µm	KOEX 814 14 µm	Tolerance Ⓢ
Nominal Thickness	µm	Internal	10	11	12	14	± 18 %
Nominal Width	mm	Internal	Various	Various	Various	Various	± 6 mm

- **Tensile properties referred to the nominal thickness:**

Parameter	Direction	Unit of measure	Method	KOEX 810 10 µm	KOEX 811 11 µm	KOEX 812 12 µm	KOEX 814 14 µm	Tolerance Ⓢ
Tensile strength at break	MD*	Kg/cm <sup>2</sup>	ASTM D882	410	413	415	420	± 10 %
Elongation at break	MD	%	ASTM D882	200	205	210	220	± 10 %
Tensile strength at break	TD**	Kg/cm <sup>2</sup>	ASTM D882	300	305	310	320	± 10 %
Elongation at break	TD	%	ASTM D882	300	305	310	320	± 10 %

\* MD = longitudinal direction; \*\* TD = transversal direction.

While we have taken all reasonable steps to verify the accuracy of the information contained in this specification, no warranties are given to this effect and purchasers should determine for themselves whether products are suitable for their own specific use. The information contained in this specification is intended for the customer it has been issued to. It must not be reproduced, or the information contained therein passed on to any third party without the written consent of Scobie & Junor.

# Product Specification



## Gas transmission rates referred to the nominal thickness:

Gas	Conditions	Unit of measure	Method	KOEX 810 10 µm	KOEX 811 11 µm	KOEX 812 12 µm	KOEX 814 14 µm	Tolerance ①
O <sub>2</sub>	23 °C, 0 % U.R.	cc/(m <sup>2</sup> *24h) bar <sup>-1</sup>	ASTM F2622 (08)	13.100	12.450	11.800	10.500	± 10 %
CO <sub>2</sub>	23 °C, 0 % U.R.	cc/(m <sup>2</sup> *24h) bar <sup>-1</sup>	ASTM F2476 (05)	88.500	84.250	80.000	70.500	± 10 %
Water vapour	38 °C 90 % U.R.	gr/( m <sup>2</sup> *24h) bar <sup>-1</sup>	ASTM F1249 (06)	1.050	1.000	950	850	± 10 %

- The “optical” characteristics are tested by the properly qualified persons as foreseen by the “Laboratory Control” and by the “Control Project of the Manufacturing Development”.

① Below stated tolerances are those used as parameter for quality controls performed at production line and/or internal laboratory and are representative of product features at the end of manufacturing process. Stated that above mentioned features might vary, being influenced by different factors such as preservation condition, transport, use and tests, quoted tolerance ranges are to be considered strictly indicative.

## 3 Use conditions

- Conditions of use:**
  - between 0 and 40 ° C (compatible with the regulations for the operation of the machine).
  - WEEGAL FILM KOEX 810 is intended only for manual use. The producer is not responsible for the packaging performances in case of use on automatic equipment.
- Maximum time of use:**
  - 12 months, from the date of packaging recorded in the cardboard box.
- Precautions for use:**
  - NOT SUITABLE FOR CONVENTIONAL OVEN OR MICROWAVE
  - Heating up to the temperatures specified in the Declaration of Conformity must be obtained in banks with controlled temperature heating;
  - It is advisable to place the coil in the machine, adjusting it first before starting the product conditioning
  - It is also advisable to remove the cardboard box only when it is ready for use and not to remove the label placed inside the core, to keep the references and be able to track the product;
  - The printed side that you can carry should not be placed in contact with food products.

While we have taken all reasonable steps to verify the accuracy of the information contained in this specification, no warranties are given to this effect and purchasers should determine for themselves whether products are suitable for their own specific use. The information contained in this specification is intended for the customer it has been issued to. It must not be reproduced, or the information contained therein passed on to any third party without the written consent of Scobie & Junor.

# Product Specification



## 4 Storage

- **Maximum storage time:** see the option "Maximum use time" in point 3
- **Storage conditions:**
  - Store in a dry place at temperatures not exceeding 35 ° C;
  - Store so that the reels do not come into contact with water, liquids, odorous substances or chemical substances in general, so as not to alter the olfactory and taste properties, in addition to avoiding any type of contamination;
  - Keep the container always intact until use;
  - It is a good rule to use warehouse stocks in rotation, based on the delivery date of the merchandise;
  - It is a good rule to activate a pest analysis system in storage tanks so as not to contaminate the product.
- **Transportation conditions:**
  - Gruppo Fabbri Svizzera guarantees the control of transport vehicles loaded in its plant, to protect the product of any type of contamination due to foreign bodies, biological agents or chemical substances, as well as damage to them.
  - It is advised that the customer check the transport vehicles used, on their own, in the eventual transfer of the merchandise to preserve the quality characteristics of the product; These controls must be based in particular on the contact with liquids / chemical substances / odorous substances / foreign bodies or biological debris, as well as on the stability of the load, to prevent damage.
- **Handling:** Avoid damaging the reels to preserve functional characteristics.


## 5 Packaging way

The product is packaged in a closed paper cardboard box with two protection plastic caps. The cardboard boxes are then placed on a pallet, which is double strapped and wrapped with a transparent film.

## 6 Sustainability

The product complies with the requirements of the following technical standards:

- UNI EN ISO 13430:2005 "Requirements for packaging recoverable by material recycling";
- UNI EN ISO 13431:2005 "Requirements for packaging recoverable in the form of energy recovery, including specification of minimum inferior calorific value".



### Customer Approval of Specification

Please sign and return this specification to [technical@scobie-junor.co.uk](mailto:technical@scobie-junor.co.uk) to confirm formal acceptance of this specification. All specifications issued will be deemed to be accepted if no communication to the contrary is received after 10 working days.

Signature:

Print name:

Position:

Date:

While we have taken all reasonable steps to verify the accuracy of the information contained in this specification, no warranties are given to this effect and purchasers should determine for themselves whether products are suitable for their own specific use. The information contained in this specification is intended for the customer it has been issued to. It must not be reproduced, or the information contained therein passed on to any third party without the written consent of Scobie & Junor.

# Product Specification



Issued by Scobie & Junor (Estd. 1919) Ltd. Certified accurate on 10/06/2021 09:24:22

While we have taken all reasonable steps to verify the accuracy of the information contained in this specification, no warranties are given to this effect and purchasers should determine for themselves whether products are suitable for their own specific use. The information contained in this specification is intended for the customer it has been issued to. It must not be reproduced, or the information contained therein passed on to any third party without the written consent of Scobie & Junor.

Scobie & Junor (Estd. 1919) Ltd, 1 Singer Road, East Kilbride, Glasgow, Scotland, G75 0XS  
www.scotnetsolutions.com email: technical@scobie-junor.co.uk