


Product Specification



Product Title: BG SHRINK BAG 400 X 600 CLEAR 95MU 400/BOX


Product Code: PM95400600

 Data Daten, Datos, Dados, Caractéristiques, данные	Standard Standard, Estándar, Padrão, Standard, Стандарт	Unit Einheit, Unidad, Unidade, Unité, Единица	Value Wert, Valor, Valor, Valeur, Значение
Product data <i>Produktdaten, Datos del producto, Dados do Produto, Caractéristiques de produit, Параметры продукта</i>			
Thickness Dicke, Espesor, Espessura, Épaisseur, Толщина	PREMIUMPACK	µm	≥ 95
Shrinkage Schrumpf, Contracción, Encolhimento, Retrait, Усадка	90°C / 2 sec	%	≥ 30
Weight per m² Gewicht pro m ² , Peso por m ² , Peso por m ² , Poids par m ² , Вес на м ²	PREMIUMPACK	g	93
Haze Trübung, Opacidad, Opacidade, Brume, Мутность	ASTM D1003-97	%	16,2
Barrier properties (permeability) <i>Barriereigenschaften (Durchlässigkeit), Propiedades de barrera (permeabilidad), Propriedades da Barreira (permeabilidade), Propriétés de la barrière (perméabilité), Барьерные свойства (проницаемость)</i>			
Oxygen (O₂) Sauerstoff, Oxígeno, Oxigênio, l'oxygène, Кислород	23°C, 50%RH	cm ³ /(m ² .24h)	0,7
Carbon dioxide (CO₂) Kohlendioxid, Dióxido de carbon, Gás carbônico, le dioxyde de carbone, Диоксид углерода	23°C, 0%RH	cm ³ /(m ² .24h)	3,5
Water vapor (H₂O) Wasserdampf, Vapor de agua, Vapor d'agua, Vapeur d'eau, Водяной пар	40°C, 90%RH	g/(m ² .24h)	7
Mechanical properties <i>Mechanische Eigenschaften, Propiedades mecánicas, Propriedades Mecânicas, Propriétés mécaniques, Механические свойства</i>			
Puncture resistance Durchstoßfestigkeit, Resistencia a la perforación, Resistência a perfuração, Résistance à la perforation, Сопротивление	ASTM F1306-16	N	155,2
Elongation at break Dehnung bis zum Durchstoß, Elongación de rotura, Alongamento para rompimento, Allongement à la rupture, Относительное удлинение	ASTM F1306-16	%	27,6
Distance to break Abstand bis zum Durchstoß, Distancia de rotura, Distância para rompimento, Distance à la rupture, Сопротивление разрыву	ASTM F1306-16	mm	13,8

While we have taken all reasonable steps to verify the accuracy of the information contained in this specification, no warranties are given to this effect and purchasers should determine for themselves whether products are suitable for their own specific use. The information contained in this specification is intended for the customer it has been issued to. It must not be reproduced, or the information contained therein passed on to any third party without the written consent of Scobie & Junor.

Product Specification



 Data Daten, Datos, Dados, Caractéristiques, данные	Standard Standard, Estándar, Padrão, Standard, Стандарт	Unit Einheit, Unidad, Unidade, Unité, Единица	Value Wert, Valor, Valor, Valeur, Значение
Energy to break Durchstoßenergie, Energía de rotura, Energia para rompimento, Energie à la rupture, Прочность на прокалывание	ASTM F1306-16	J	0,913
Stiffness Steifheit, Rigidez, Rigidez, Rigidité, жесткость	ASTM F1306-16	N/mm	26,5
Recommended conditions (depending on machine type) <i>Empfohlene Bedingungen (abhängig vom Maschinentyp), Condiciones recomendadas (dependiendo del tipo de máquina), Condições Recomendadas (variável de acordo com a máquina), Conditions recommandées (selon le type de machine), Рекомендуемые условия на использование (зависит от типа оборудования)</i>			
Sealing time Schweißzeit, Tiempo de sellado, Tempo de selagem, Temps de soudure, Время сваривания	PREMIUMPACK	s	min. 2
Shrink condition – time Schrumpfen – Zeit, Estado de contracción - tiempo, Condições de encolhimento – Tempo, Temps de rétractation, Время усадки	PREMIUMPACK	s	1-2
Shrink condition – temperature Schrumpfen – Temperatur, Estado de contracción: temperatura, Condições de encolhimento – Temperatura, Température de rétractation, Температура усадки	PREMIUMPACK	°C	90-95
Storage conditions <i>Lagerbedingungen, Condiciones de almacenamiento, Condições de Armazenamento, Conditions de stockage, Условия хранения</i>			
Time Zeit, Tiempo, Tempo, Temps, Срок годности	2 years after production, 2 Jahre nach Produktionsdatum, 2 años después de la producción, 2 anos após a produção, 2 ans après la production, 2 года после даты производства		
Conditions Bedingungen, Condiciones, Condições, Conditions, Условия хранения	≤ 23°C, ≤ 60% RH original packaging, Originalverpackung, envase original, na embalagem original, Emballage d'origine, в оригинальной упаковке		

Note: The information and data contained in this document are believed to be correct and are given in good faith. However, no liability, warranty or guarantee of the performance is created by this document. The specified values are averages. Valid until further notice.

While we have taken all reasonable steps to verify the accuracy of the information contained in this specification, no warranties are given to this effect and purchasers should determine for themselves whether products are suitable for their own specific use. The information contained in this specification is intended for the customer it has been issued to. It must not be reproduced, or the information contained therein passed on to any third party without the written consent of Scobie & Junor.

Product Specification



Customer Approval of Specification

Please sign and return this specification to **technical@scobie-junor.co.uk** to confirm formal acceptance of this specification. All specifications issued will be deemed to be accepted if no communication to the contrary is received after 10 working days.

Signature:

Print name:

Position:

Date:

Issued by Scobie & Junor (Estd. 1919) Ltd. Certified accurate on 20/04/2022 13:34:11

While we have taken all reasonable steps to verify the accuracy of the information contained in this specification, no warranties are given to this effect and purchasers should determine for themselves whether products are suitable for their own specific use. The information contained in this specification is intended for the customer it has been issued to. It must not be reproduced, or the information contained therein passed on to any third party without the written consent of Scobie & Junor.