

Product Specification

Product Title: CLING FILM 450MM 10 MICRON 1500MTR/ROLL

Product Code: PP10450

Composition of Film*

PVC

Primer Plasticizer

Seconder Plasticizer

Additives

*This film's correction number is 3. (Factor 3 formula.)



Property	Value	Unit	Test Method
Density	1,24	g/ cm ³	D 792
Thickness	9-10	± %10 μ	F 2251
Yield	73-90	m ² /kg	
Roll Lenght	800-2000	-0/+1,5 % mt	
Range	150-1300	± 5 mm	
Core ID φ	76,110	mm	
Colour	Transparent, Violet, Pink		

Tensile	MD	27	± %3	N/mm ²	ASTM D882
	TD	25			
Elongation	MD	145	± %3	%	ASTM D882
	TD	148			
Oxygen transmission (O ₂)	23 ° C	7600	± %20	cm ³ /m ² .24h.1atm	ASTM D3985
Carbon dioxide transmission (CO ₂)	23 ° C	55200	± %20	cm ³ /m ² .24h.1atm	
Water vapour transmission (H ₂ O)	23 ° C	185	± %20	g/m ² .24h.1atm	
Total Migration		≤ 10 ± %3	mg/dm ²	Turkish Food Codex Communiqué on Contact with Food Ingredients 2013/34 and Commission Regulation EU No: 10/2011 10 days, 40 ° C	

There is no allergenic content and microbiological tests are safe.

Store in dry conditions between 15 ° C and 25 ° C. Do not expose to direct sun. The maximum recommended storage is 12 months.

While we have taken all reasonable steps to verify the accuracy of the information contained in this specification, no warranties are given to this effect and purchasers should determine for themselves whether products are suitable for their own specific use. The information contained in this specification is intended for the customer it has been issued to. It must not be reproduced, or the information contained therein passed on to any third party without the written consent of Scobie & Junor.

Product Specification



Conformities

Compliance with Foodstuffs according to Art. 16 of EU Regulation 1935/2004, Annex IV of EU Regulation 10/2011.

It has been manufactured in accordance with the relevant requirements of 2023/2006 on good manufacturing practice for materials and articles to come into contact with food.

Film without Phthalate and without Bisphenol A.

The VCM monomer content is less than 1 ppm.

Not suitable for conventional ovens.

The characteristic listed are average values to be used for information and therefore subject to possible variations.

Customer Approval of Specification	
Please sign and return this specification to technical@scobie-junor.co.uk to confirm formal acceptance of this specification. All specifications issued will be deemed to be accepted if no communication to the contrary is received after 10 working days.	
Signature:	
Print name:	
Position:	
Date:	

Issued by Scobie & Junor (Estd. 1919) Ltd. Certified accurate on 14/12/2021 12:27:41

While we have taken all reasonable steps to verify the accuracy of the information contained in this specification, no warranties are given to this effect and purchasers should determine for themselves whether products are suitable for their own specific use. The information contained in this specification is intended for the customer it has been issued to. It must not be reproduced, or the information contained therein passed on to any third party without the written consent of Scobie & Junor.