

Technical Data Sheet **McAirlaid's**



Quality

SuperCore® MP-SL

Design

P

Recipe

Pulp	50,0 %
Superabsorber	15,0 %
Films	35,0 %
Man Made Fibres	0,0 %
Nonwoven	0,0 %
Other	

	Value	Methode
Total Basis Weight	120 g/m ²	McA 02.10
Tensile strength dry	0,64 KN/m	McA 03.10
Elongation dry	47 %	McA 03.10
Tensile strength wet	0,65 KN/m	McA 03.20
Elongation wet	51 %	McA 03.20
Caliper 1-ply	0,86 mm	McA 04.10
Density	140 Kg/m ³	McA 07.10
Stiffness	128 mm	McA 06.10
Absorption Time *	sec.	McA 08.10
Vertical Absorbency*	96 mm	McA 05.10

